

TL-50D

立鐸下進專用鐸條

相當規格：


AWS A5.1 E7048
EN ISO 2560-B-4948-A
JIS Z 3211 E4948

特性與用途：

TL-50D是490N/mm²級高張力低氫系填角鐸立鐸下進專用鐸條，其熔渣的控制性良好，故在角鐸及鐸接操作困難的地方，可顯示其優點，機械性能優異，耐龜裂性佳，鐸渣剝離性良好。適用於船體、鋼架結構物和橋樑鐸接。

注意事項：

- (1) 立角鐸下進時鐸條與母材兩側成45°與鐸道成60~80°夾角如圖示，起弧端輕靠由上而下鐸不宜採用擺弧方式鐸接。
- (2) 使用前鐸條應先於300~350°C烘乾約30~60分鐘。
- (3) 母材表面的水份、銹漬、油污、要充分去除，以防止氣孔及龜裂的產生。
- (4) 電流太大入熱量過高時，會引起衝擊值低下，宜特別注意選用適當之電流。




鐸道化學成份之一例(wt%)：

C	Mn	Si	P	S
0.08	1.00	0.55	0.02	0.006

鐸道機械性質之一例：

降伏強度 MPa(ksi)	抗拉強度 MPa(ksi)	伸長率 %	衝擊值J (ft-lbf) -30°C (-20°F)
500(73)	600(87)	28	78(58)

鐸接位置：



適用電流範圍：(AC或DC+)

直徑及長度(mm)		3.2x350	4.0x450	5.0x450
電流範圍 (Amps)	立鐸 下進	110-160	140-210	210-240

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.